



Material: **API II ABS 960**

Product Description: API II ABS 960 is a very high impact grade with medium flow.

Property	Data	Unit	Test Method
Mechanical			
Tensile Strength at Yield	5,900	psi	ASTM D 638
Tensile Modulus	280,000	psi	ASTM D 638
Flexural Modulus	295,000	psi	ASTM D 790
Impact			
Izod Impact Strength @ 73°F	8.0 *	ft.lbs./inch	ASTM D 256
Thermal			
Vicat Softening Point	201	deg. F	ASTM D 1525
Deflection Temperature (annealed) @ 264 psi	203	deg. F	ASTM D 648
Physical			
Melt Flow (200°C / 5.0 KG)	0.1	gr./ 10 min.	ASTM D 1238
Melt Flow (230°C / 3.8 KG)	1.7	gr./ 10 min.	ASTM D 1238
Specific Gravity	1.03	gr./ cc	ASTM D 892

* Test results obtained using 1/8 inch notched injection molded specimen

The test results and property values listed have been obtained using laboratory controlled test methods. These values are intended to be a guide only. They are offered without guarantee since conditions under which our product is used are beyond our control. API II, therefore, disclaims any liability for loss or damage incurred in connection with this products use. Rev 07/08

API II, INC.

11421 Labrador Lane, Concord, OH 44077
440-725-9019

WWW.API2.NET