



**Material:** **API II 370**

**Product Description:** API II 370 is a high heat polystyrene produced in pellet form. It has excellent strength and clarity as well as fast set-up properties.

**Application:** Used in the manufacture of containers, housewares, and medical applications. Processing methods include blow molding, extrusion and injection molding. Complies with FDA regulation 21 CFR 177.1640.

Property	Data	Unit	Test Method
<b>Mechanical</b>			
Tensile Strength at Failure	7,350	psi	ASTM D 638
Tensile Modulus	425,000	psi	ASTM D 638
Elongation at Failure	3.0	%	ASTM D 638
Rockwell Hardness	90	L Scale	ASTM D 785
<b>Impact</b>			
Izod Impact Strength	0.35 *	ft.lbs./inch	ASTM D 256
<b>Thermal</b>			
Vicat Softening Point	220	deg. F	ASTM D 1525
Deflection Temperature (annealed) @ 264 psi	200	deg. F	ASTM D 648
<b>Physical</b>			
Melt Flow (Condition G)	3.0	gr./ 10 min.	ASTM D 1238
Specific Gravity	1.05	gr./ cc	ASTM D 892

\* Test results obtained using 1/8 inch notched injection molded specimen

The test results and property values listed have been obtained using laboratory controlled test methods. These values are intended to be a guide only. They are offered without guarantee since conditions under which our product is used are beyond our control. API II, therefore, disclaims any liability for loss or damage incurred in connection with this products use. Rev 05/08

## API II, INC.

11421 Labrador Lane, Concord, OH 44077  
440-725-9019

[WWW.API2.NET](http://WWW.API2.NET)